

# Ethanol synthesis from carbon dioxide on TiO<sub>2</sub>-supported [Rh<sub>10</sub>Se] catalyst

Hiroshi Kurakata, Yasuo Izumi\* and Ken-ichi Aika\*

Department of Environmental Chemistry and Engineering, Interdisciplinary Graduate School of Science and Engineering, Tokyo Institute of Technology, 4259 Nagatsuta, Midori-ku, Yokohama 226, Japan

Supported [Rh<sub>10</sub>Se] catalyst on TiO<sub>2</sub> converted carbon dioxide into ethanol faster ( $60 \times 10^{-3} \text{ mol h}^{-1} \text{ g cat}^{-1}$ ) and more selectively ( $\approx 83\%$ ) than other supported Rh clusters or [Rh<sub>10</sub>Se] on other inorganic oxides, presumably due to the effects of interstitial Se and the interface of the [Rh<sub>10</sub>Se] cluster and TiO<sub>2</sub>.

Recent environmental conditions require the development of effective catalysts for the reduction of NO<sub>x</sub>, CO<sub>2</sub>, SO<sub>x</sub>, benzene, etc. Compared to conventional rhodium catalysts known to produce methane (and other hydrocarbons) from CO<sub>2</sub> + H<sub>2</sub>,<sup>1</sup> we have concentrated on rhodium-based catalysts which convert CO<sub>2</sub> into ethanol. Some examples of oxygenate syntheses (methanol, acetaldehyde, etc.) from CO + H<sub>2</sub> over Rh catalysts are known, but their activities are very low ( $3.5 \times 10^{-5}$ – $2.3 \times 10^{-2} \text{ min}^{-1}$ ,  $\approx 673 \text{ K}$ ).<sup>2–4</sup> There are some reports of ethanol synthesis from CO<sub>2</sub>/H<sub>2</sub>, but here also activities and selectivities were low.<sup>5</sup> In this study, we report on an efficient synthesis of ethanol from CO<sub>2</sub>/H<sub>2</sub> over supported [Rh<sub>10</sub>Se] clusters prepared from [Rh<sub>10</sub>Se(CO)<sub>22</sub>]<sup>2–</sup>.<sup>6,7</sup> The promoter effect of interstitial Se (inside the [Rh<sub>10</sub>] framework) for ethanol synthesis was considered.

[N(PPh<sub>3</sub>)<sub>2</sub>]<sub>2</sub>[Rh<sub>10</sub>Se(CO)<sub>22</sub>] **1**, [PhCH<sub>2</sub>NMe<sub>3</sub>]<sub>2</sub>[Rh<sub>6</sub>C(CO)<sub>15</sub>] **2** and Rh<sub>6</sub>(CO)<sub>16</sub> **3** were supported on inorganic oxides by reaction at 290 K (2 h) in purified THF in Ar atmosphere, with subsequent removal of THF. TiO<sub>2</sub> (Aerosil P25), Al<sub>2</sub>O<sub>3</sub> (Aerosil alon C) and SiO<sub>2</sub> (Fuji Silysia silica gel no. 952) were treated at 573 K for 2 h under vacuum prior to use as supports. MgO was prepared from Mg(OH)<sub>2</sub> (99.99%) by treatment at 773 K for 2 h in vacuum. The loadings of Rh were fixed to 1.3 mass% Rh for TiO<sub>2</sub> and Al<sub>2</sub>O<sub>3</sub>, 2.8 mass% for SiO<sub>2</sub>, and 1.6 mass% for MgO. The supported [Rh<sub>10</sub>Se], [Rh<sub>6</sub>C] and [Rh<sub>6</sub>] clusters prepared from **1**, **2** and **3** are denoted [Rh<sub>10</sub>Se]/oxide, [Rh<sub>6</sub>C]/oxide and [Rh<sub>6</sub>]/oxide, respectively. The incipient supported clusters were totally decarbonylated (checked by GC) by heating in vacuum at 593–813 K. TiO<sub>2</sub> was impregnated with Rh(NO<sub>3</sub>)<sub>3</sub> in aqueous solution, followed by treatments in air (1 h), then in H<sub>2</sub> (1 h) at 523 K (Rh/TiO<sub>2</sub>). CO<sub>2</sub> hydrogenation was carried out under 47 kPa of CO<sub>2</sub> + H<sub>2</sub> (CO<sub>2</sub>:H<sub>2</sub> = 1:2) in the temperature range 523–723 K ( $T_{\text{react}}$ ) in a closed circulating system (dead volume 210 cm<sup>3</sup>). The reaction products were analysed by a gas chromatograph using a column of Unibeads C for CH<sub>4</sub>, Porapak Q for CO<sub>2</sub> and hydrocarbons and dioctyl sebacate for ethanol at 353 K.

Depending on the nature of supporting oxide, the supported [Rh<sub>10</sub>Se] clusters exhibited a sharp variation in the activity and selectivity of CO<sub>2</sub> hydrogenation. After pretreatment in vacuum (total decarbonylation) at 623–653 K, the [Rh<sub>10</sub>Se]/TiO<sub>2</sub> produced ethanol ( $3.7 \times 10^{-3} \text{ mol h}^{-1} \text{ g cat}^{-1}$ ) (and some methane) (Table 1 entry b); however, no ethanol was produced on [Rh<sub>10</sub>Se] supported on Al<sub>2</sub>O<sub>3</sub>, MgO or SiO<sub>2</sub> (Table 1, entries h–j). The [Rh<sub>10</sub>Se]/SiO<sub>2</sub> system showed no activity.

The reaction and preheating conditions were varied for the [Rh<sub>10</sub>Se]/TiO<sub>2</sub> catalyst. According to the increase of  $T_{\text{react}}$  from 523 to 723 K, the rate of ethanol synthesis increased to  $6.0 \times 10^{-3} \text{ mol h}^{-1} \text{ g cat}^{-1}$ , but the selectivity decreased from 83 to 51% (Table 1, entries a–c). The preheating temperature ( $T_{\text{evac}}$ ) was also varied in the range 523–813 K. In the CO<sub>2</sub>/H<sub>2</sub> reaction

at 623 K, the ethanol synthesis rate at  $T_{\text{evac}} = 813 \text{ K}$  was 57% of that at  $T_{\text{evac}} = 623 \text{ K}$  (Table 1, entries b, f), and the rate at  $T_{\text{evac}} = 523 \text{ K}$  was only 26% of that at  $T_{\text{evac}} = 623 \text{ K}$ . Use of a trap (193 K) in the closed circulating system (Table 1, entry d) led to a decrease in synthesis rate to 38% compared to the case without a trap (Table 1, entry b) probably due to a poisoning effect of the product. Ethanol formation was also checked by mass spectrometry for the [Rh<sub>10</sub>Se]/TiO<sub>2</sub> system: peaks of EtOH ( $m/z$  31, 45, 27) and CH<sub>4</sub> ( $m/z$  16, 15) grew as the reaction proceeded, while peaks at  $m/z$  44 (CO<sub>2</sub>) and 2 (H<sub>2</sub>) diminished gradually. From CO + H<sub>2</sub> (36 kPa), [Rh<sub>10</sub>Se]/TiO<sub>2</sub> produced methane ( $3.1 \times 10^{-4} \text{ mol h}^{-1} \text{ g cat}^{-1}$ ) besides CO<sub>2</sub> and C<sub>2</sub>H<sub>6</sub> at 623 K. The total activity ( $4.6 \times 10^{-4} \text{ mol h}^{-1} \text{ g cat}^{-1}$ ) was lower than for CO<sub>2</sub> hydrogenation under the same conditions ( $5.1 \times 10^{-3} \text{ mol h}^{-1} \text{ g cat}^{-1}$ , Table 1, entry b). It is interesting that a strong hydrogen isotope effect was observed for ethanol synthesis ( $r_{\text{CO}_2 + \text{D}_2}/r_{\text{CO}_2 + \text{H}_2} \approx 0.2$ – $0.3$ ). As (almost) no isotope effect was detected for CH<sub>4</sub> production, the activated reaction process of CO<sub>2</sub> with CH<sub>x</sub>(a), probably at the interface between [Rh<sub>10</sub>Se] and TiO<sub>2</sub>, may be a cause for the selective ethanol synthesis. The causes of selective reaction of adsorbed species from CO<sub>2</sub> with CH<sub>x</sub>(a) (EtOH formation), rather than with H(a) (CH<sub>4</sub> formation) over [Rh<sub>10</sub>Se]/TiO<sub>2</sub> is under investigation by FTIR studies.

Next we studied other Rh clusters (or salts) for their catalytic activity supported on TiO<sub>2</sub>. The Rh cluster containing interstitial carbon [Rh<sub>6</sub>C] on TiO<sub>2</sub> produced ethanol ( $0.4 \times 10^{-3} \text{ mol h}^{-1} \text{ g cat}^{-1}$ , Table 2, entry b); only 11% that of [Rh<sub>10</sub>Se]/TiO<sub>2</sub> ( $T_{\text{evac}} = 623 \text{ K}$ ), and the selectivity was also lower (10%, Table 2, entry b). The [Rh<sub>6</sub>]/TiO<sub>2</sub> and conventional Rh/TiO<sub>2</sub> from Rh(NO<sub>3</sub>)<sub>3</sub> produced only methane (Table 2, entries c, d). The presence of an interstitial atom (Se or C) in the Rh cluster framework may be of importance in ethanol synthesis.

We measured the Rh K-edge EXAFS spectra for the catalysts (KEK-PF, Tsukuba, proposal no. 95G226). For [Rh<sub>10</sub>Se]/TiO<sub>2</sub>, the coordination number ( $N$ ) of the Rh–Rh bonds was found to

**Table 1** The reaction rates of CO<sub>2</sub> hydrogenation over [Rh<sub>10</sub>Se] clusters supported on TiO<sub>2</sub>, Al<sub>2</sub>O<sub>3</sub>, MgO and SiO<sub>2</sub><sup>a</sup>

Entry	Support	$T_{\text{evac.}}/\text{K}$	$T_{\text{react.}}/\text{K}$	Initial rate/ $10^{-3} \text{ mol h}^{-1} \text{ g cat}^{-1}$		EtOH select./%
				EtOH	CH <sub>4</sub>	
a	TiO <sub>2</sub>	623	523	1.9	0.4	83
b <sup>b</sup>		623	623	3.7	1.4	71
c		623	723	6.0	5.8	51
d <sup>c</sup>		623	623	1.4	1.9	42
e		813	523	0.9	0.4	71
f	Al <sub>2</sub> O <sub>3</sub>	813	623	2.1	1.4	59
g		813	723	4.7	5.9	42
h		653	623	0	0.15	0
i		623	623	0	0.039	0
j		623	623	0	0	0

<sup>a</sup> Cluster catalysts were evacuated at the temperature indicated then in H<sub>2</sub> at 623 K before catalysis. <sup>b</sup> The corresponding carbon dioxide consumption was  $9.0 \times 10^{-3} \text{ mol h}^{-1} \text{ g cat}^{-1}$ . <sup>c</sup> Using a dry ice–acetone (193 K) trap.

**Table 2** The reaction rates of CO<sub>2</sub> hydrogenation at 623 K over several Rh clusters (or salts) supported on TiO<sub>2</sub>

Entry	Cluster	$T_{\text{evac.}}/\text{K}$	Initial rate/ $10^{-3} \text{ mol h}^{-1} \text{ g}_{\text{cat}}^{-1}$			
			EtOH	CH <sub>4</sub>	Other hydrocarbons <sup>a</sup>	EtOH select./%
a	[Rh <sub>10</sub> Se(CO) <sub>22</sub> ] <sup>2-</sup>	623	3.7	1.4	0	71
b	[Rh <sub>6</sub> C(CO) <sub>15</sub> ] <sup>2-</sup>	673	0.4	1.2	2.4	10
c	Rh <sub>6</sub> (CO) <sub>16</sub>	593	0	6.2	0	0
d <sup>b</sup>	Rh(NO <sub>3</sub> ) <sub>3</sub>	—	0	1.8	0	0

<sup>a</sup> Ethene and ethane. <sup>b</sup> In O<sub>2</sub>/H<sub>2</sub> at 523 K prior to catalysis.

be 4.8 when preheated at 523 K; the same value as in the [Rh<sub>10</sub>Se(CO)<sub>22</sub>]<sup>2-</sup> crystal (bicapped square-antiprismatic).<sup>6,7</sup> The Se:Rh ratio did not change upon supporting and heating of the catalyst, based on the edge jump for Se K-edge XANES; hence, we believe that the cluster framework unit [Rh<sub>10</sub>Se] remained intact. Examples of supported clusters of Ru, Rh, Re or Os attached through metal (M)–surface oxygen [O<sub>(s)</sub>] bonds (2.00–2.24 Å) have been reported.<sup>8</sup> The present [Rh<sub>10</sub>Se] cluster is attached with  $r_{\text{Rh-O(s)}}$  2.07–2.18 Å in accord with the above. By raising  $T_{\text{evac.}}$  to 623 K,  $N_{\text{Rh-Rh}}$  decreased from 4.8 to 4.0 whereas  $N_{\text{Rh-O(s)}}$  increased from 1.2 ( $T_{\text{evac.}} = 523 \text{ K}$ ) to 1.5 (623 K). One explanation of these changes of  $N$  is if one triangular face of [Rh<sub>10</sub>Se] is attached to the TiO<sub>2</sub> surface at  $T_{\text{evac.}} = 523 \text{ K}$ , and if upon heating to 623 K [Rh<sub>10</sub>Se] is transformed from a bicapped square-antiprismatic geometry to a relatively flat shape by cleavage of Rh–Rh bonds of the triangular face and by additional formation of Rh–O<sub>(s)</sub> bonds. By raising  $T_{\text{evac.}}$  further to 673–813 K,  $N_{\text{Rh-Rh}}$  further decreased as did the synthesis rate (Table 1). Hence, the [Rh<sub>10</sub>Se] catalyst with  $N_{\text{Rh-Rh}} = 4.0$  seems to have the optimum ('fried egg') structure for catalysis.  $N_{\text{Rh-Rh}}$  values were smaller (2.7–3.3) for [Rh<sub>10</sub>Se]/Al<sub>2</sub>O<sub>3</sub>, [Rh<sub>10</sub>Se]/MgO or [Rh<sub>10</sub>Se]/SiO<sub>2</sub> at  $T_{\text{evac.}} = 623$ –653 K compared to those for [Rh<sub>10</sub>Se]/TiO<sub>2</sub> (4.0–4.8).  $N_{\text{Rh-Rh}}$  values for [Rh<sub>6</sub>C]/TiO<sub>2</sub>, [Rh<sub>6</sub>]/TiO<sub>2</sub> and Rh/TiO<sub>2</sub> were 7–10, indicating the formation of aggregated Rh particles.

Besides Rh K-edge EXAFS, corresponding results were obtained for supported [Rh<sub>10</sub>Se] samples by Se K-edge EXAFS ( $r_{\text{Se-Rh}} = 2.42 \pm 0.01 \text{ Å}$ ) and XANES (spectra similar to Rh<sub>3</sub>Se<sub>8</sub> alloy<sup>9</sup>), supporting the 'fried egg' structure of [Rh<sub>10</sub>Se].

Three controlling factors are thus proposed for preferential ethanol synthesis, (i) the structural effect of a 'fried-egg' [Rh<sub>10</sub>Se] framework, (ii) the electronic effect of interstitial Se (oxidation state –2 by XPS and XANES), and (iii) the support effect of TiO<sub>2</sub>.

## References

- 1 T. Iizuka, Y. Tanaka and K. Tanabe, *J. Mol. Catal.*, 1982, **17**, 381.
- 2 T. Koerts, W. J. J. Welters and R. van Santen, *J. Catal.*, 1992, **134**, 1.
- 3 T. J. Lee and B. C. Gates, *J. Mol. Catal.*, 1992, **71**, 335.
- 4 T. Inoue, T. Iizuka and K. Tanabe, *Appl. Catal.*, 1989, **46**, 1.
- 5 N. Ikehara, K. Hara, A. Satsuma, T. Hattori and Y. Murakami, *Chem. Lett.*, 1994, **2**, 263.
- 6 G. Ciani, L. Garlaschelli and A. Sironi, *J. Chem. Soc., Chem. Commun.*, 1981, 563.
- 7 D. Galli, L. Garlaschelli, G. Ciani, A. Fumagalli, S. Martinengo and A. Sironi, *J. Chem. Soc., Dalton Trans.*, 1984, 55.
- 8 Y. Izumi and Y. Iwasawa, *Chemtech*, 1994, July, 20.
- 9 D. Hohnke and E. Parthé, *Z. Kristallogr.*, 1968, **127**, 164.

Received, 24th October 1995; Com. 5/07020A